

Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Original) A glass comprising following components by mass%.

P_2O_5	5-25%
$BaO+SrO$	21-50%
Nb_2O_5	35-65%
$Li_2O+Na_2O+K_2O$	0-3%

2. (Currently Amended) ~~The~~A glass ~~as claimed in claim 1, further~~ comprising following components by mass%.

P_2O_5	5-25%
B_2O_3	0-15%
SiO_2+GeO_2	0-5%
$BaO+SrO$	21-50%
$MgO+CaO$	0-25%
Nb_2O_5	35-65%
TiO_2	0-15%
Ta_2O_5	0-15%
Bi_2O_3	0-15%
ZnO	0-15%
WO_3	0-15%
$Y_2O_3+La_2O_3+Gd_2O_3$	0-15%
$Li_2O+Na_2O+K_2O$	0-3%
Al_2O_3	0-5%

Sb_2O_3 0-0.5%

3. (Currently Amended) ~~The~~A glass as ~~claimed in claims 1 or 2, further~~ comprising following components by mass%;

P_2O_5	5-20%
B_2O_3	0-10%
$\text{SiO}_2+\text{GeO}_2$	0-5%
BaO	21-50%
$\text{MgO}+\text{CaO}$	0-25%
Nb_2O_5	35-65%
TiO_2	0-15%
Ta_2O_5	0-15%
Bi_2O_3	0-15%
ZnO	0-15%
WO_3	0-15%
$\text{Y}_2\text{O}_3+\text{La}_2\text{O}_3+\text{Gd}_2\text{O}_3$	0-15%
$\text{Li}_2\text{O}+\text{Na}_2\text{O}+\text{K}_2\text{O}$	0-3%
Al_2O_3	0-5%
Sb_2O_3	0-0.5%

wherein $\text{Nb}_2\text{O}_5/(\text{BaO}+\text{SrO})$ is 0.85-2.20.

4. (Currently Amended) The glass as claimed in ~~any one of claims 1 to 3~~ claim 1, wherein the glass is substantially free from PbO component.

5. (Currently Amended) The glass as claimed in ~~any one of claims 1 to 4~~ claim 1,

having a dielectric constant of 15 or more.

6. (Currently Amended) The glass as claimed in ~~any one of claims 1 to 5~~ claim 1,
having a dielectric loss of 10.0×10^{-4} or less.

7. (Currently Amended) The glass as claimed in ~~any one of claims 1 to 6~~ claim 1,
having an electrical resistivity of $1.0 \times 10^{16} \Omega \cdot \text{cm}$ or more.

8. (Currently Amended) A glass substrate consisting of the glass as claimed in ~~any one of claims 1 to 7~~ claim 1.

9.(New) The glass as claimed in claim 2, wherein the glass is substantially free from PbO component.

10.(New) The glass as claimed in claim 2, having a dielectric constant of 15 or more.

11.(New) The glass as claimed in claim 2, having a dielectric loss of 10.0×10^{-4} or less.

12.(New) The glass as claimed in claim 2, having an electrical resistivity of $1.0 \times 10^{16} \Omega \cdot \text{cm}$ or more.

13.(New) A glass substrate comprising the glass as claimed in claim 2.

14.(New) The glass as claimed in claim 3, wherein the glass is substantially free from

PbO component.

15.(New) The glass as claimed in claim 3, having a dielectric constant of 15 or more.

16.(New) The glass as claimed in claim 3, having a dielectric loss of 10.0×10^{-4} or less.

17.(New) The glass as claimed in claim 3, having an electrical resistivity of 1.0×10^{16} $\Omega \cdot \text{cm}$ or more.

18.(New) A glass substrate comprising the glass as claimed in claim 3.